

# TECHNICAL DATA SHEET



<b>Product name</b>	<b>Revised</b>
GENAN 80 Mesh	01.11.2025

<b>Product description</b>
Free-flowing, homogenous and uniform, black rubber powder derived from end-of-life tyres through cryogenic milling. As anti-caking agent, 0.5% SiO <sub>2</sub> (Ultrasil®VN3) is added.

<b>Contact Data of Manufacturer</b>						
Plant:	Genan A/S Jegindøvej 16 DK-8800 Viborg Denmark	Genan GmbH Gottlieb-Daimler Straße 34 D-46282 Dorsten Germany	Betriebsstätte Oranienburg: Birkenallee 80 D-16515 Oranienburg Germany	Betriebsstätte Kammlach: Im Gewerbepark Unterallgäu 1 D-87754 Kammlach Germany	Genan, S.A. Lugar da Pardala Estrada Nacional 109, Km 31 PT-3880-728 São João de Ovar Portugal	Genan Inc. 18038 Beaumont Hwy. Houston TX77049 USA
Tel.:	+45 8728 3000	+49 2362 9527 0	+49 3301 578 0	+49 8261 7369 0	+351 256 580 600	+1 713 6748500
Fax:		+49 2362 9257 150	+49 3301 578 150	+49 8261 7369 150		+1 713 6748501
E-mail:	info-dk@genan.com	info-de@genan.com			info-pt@genan.com	info-us@genan.com

<b>Typical properties</b>			<b>80 Mesh</b>	<b>80 Mesh</b>
			<b>0-180 µm (V1)</b>	<b>125-180 µm (V2)</b>
Properties	Test methods	Unit	Typical values	Typical values
Specific density	ASTM D1817	kg/m <sup>3</sup>	1.160	1.160
Bulk density	EN 1097-3	kg/m <sup>3</sup>	435	410
Particle size range	ASTM D5644	µm	0-180	125-180
Particles > 180 µm (max. 10%)	ASTM D5644	%	< 5	< 8
Total polymer content (RCH)	ISO 9924-1	%	≥ 50	≥ 50
Ash content	ISO 9924-1	%	8	8
Carbon black	ISO 9924-1	%	30	30
Moisture content (Loss: 2h @ 105°C)	ASTM D1509	%	< 2	< 2
Impurities	Internal test method (Note 1)	%	<0,01	<0,01
PAH 8 REACH	AfPS GS 2019:01 PAK	mg/kg	< 20	< 20

Note 1: The internal test method is based on Genan's expertise and on the international standards ASTM D5603 and EN14243-2.

<b>Remarks</b>	
Particle size distribution	Information on the actual particle size distribution is available on the relevant sieve curves, which can be downloaded from the Genan website. Alternatively, our sales department can forward upon request.
Impurities	GENAN 80 Mesh is a recycled product manufactured with end-of-life tyres as feedstock. Free impurities in the form of metal, textile, minerals, small stones, plastic and wood may thus occur.
Agglomeration	GENAN 80 Mesh may due to its physical properties - and depending on weather / storage conditions - have a tendency to cake over time. Storage as recommended in section 7.2 of the safety data sheet for this product.
Environment, Health & Safety	Guidelines in relation to environmental impact, health and safety are stated in the relevant Safety Data Sheet as well as in the applicable Instructions for Use and Disposal - both of which can be downloaded from the Genan website. Alternatively, our sales department can forward upon request.

Characteristics stated are typical for the product. The product is derived from a large number of different tyres; consequently, Genan cannot give any exact values on the chemical composition of the material. The above-mentioned characteristics and values have been prepared to the best of our knowledge, and Genan shall not be liable for any insufficiency or inaccuracy in such information.

## CERTIFICATIONS

### Genan A/S

ISO 9001:2015  
ISO 14001:2015  
ISO 45001:2018  
ISO 50001:2018

### Genan GmbH

ISO 9001:2015  
ISO 14001:2015  
ISO 45001:2018  
ISO 50001:2018

### Genan Inc.

ISO 9001:2015  
ISO 14001:2015  
ISO 45001:2018  
ISO 50001:2018

### Genan, S.A.

ISO 9001:2015  
ISO 14001:2015  
ISO 45001:2018  
ISO 50001:2018